



drs-guarnizioni.it

RUBBER	HARDNESS		COLORATION	MAIN AREAS OF APPLICATION	TEMPERATURE OF USE
	FROM	TO			
NBR (nitrile)	40	90	All	Appliance, automotive, various applications	- 15°C + 100°C
EPDM (dutral)	30	90	All	Automotive, drinking water, lighting	- 20°C + 130°C
SBR	40	85	All	Non-potable water, automotive	- 30°C + 80°C
NR (natural)	40	85	Limited range	Automotive, various applications	- 40°C + 70°C
CR (neoprene)	40	80	Limited range	Lighting, coatings, insulation	- 20°C + 85°C
HNBR	50	90	All	Gas, automotive, hydraulic	- 20°C + 150°C
ACM (polyacrylic)	50	80	Limited range	Automotive	- 20°C + 160°C
FKM (viton)	50	95	Limited range	Automotive, boilers, petrochemical	- 0°C + 200°C
VMQ (silicone)	20	80	All	Automotive, lighting, pharmaceutical	- 60°C + 180°C
FVMQ (fuorosilicone)	40	80	Limited range	Automotive, lighting, pharmaceutical	- 60°C + 180°C